

Technical Data Sheet

Sustarin[®] C - ASTM

POM-C

Typical characteristics

- Chemical resistant
- Good dimensional stability
- Low moisture absorption
- Good sliding properties

Typical industries

- Mechanical Engineering Industry
- Conveyor Technology & Automation
- Food Industry
- Oil and Gas

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	1.41
Water Absorption 24 hours	ASTM D570	%	0.2
Dissipation Factor	ASTM D150	1MHz	0.004
Water Absorption Saturation	ASTM D570	%	0.9
Mechanical properties			
Hardness	ASTM D2240	Shore D	85
Tensile Strength at yield 73°F	ASTM D638	psi	9500
Tensile Modulus	ASTM D638	psi	400000
Elongation at Break	ASTM D638	%	40
Flexural Strength	ASTM D790	psi	12000
Flexural Modulus	ASTM D790	psi	400000
Compressive Strength	ASTM D695	psi	15000
Rockwell Hardness	ASTM D785		88
Rockwell Hardness	ASTM D785	R	120
Shear Strength	ASTM D732	psi	8000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.21
Thermal properties			
Thermal Conductivity		in/hr/ft ² /°F	1.6
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	5.5

ri-inquiry@roebling.com • www.roebling.com/industrial/materials

Print: 17/08/2026 • Release: 08/04/2024 • Version: 1.0
PIM-ID: 717933 • PIM-Code: 42-15-35.153.12.223-5.11.5.5-2
Company-IDs: 23070

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Melting Point		°F	330
Continuous Service Temperature, Air		°F	180
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	225
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	320
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	3.8
Dielectric strength	ASTM D149	V/mil	450
Surface resistivity	ASTM D257	Ω/cm	10 ¹⁶
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 17/08/2026 • Release: 08/04/2024 • Version: 1.0
PIM-ID: 717933 • PIM-Code: 42-15-35.153.12.223-5.11.5.5-2
Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

